

Cadeby White



Technical Data

Description	Hard and durable limestone with light bedding
Country of Origin	UK
Geological Type	Magnesian Limestone
Colour	Light Bronze-white
Density	2150 kg/m ³
Compressive Strength	68.9
Water Absorption	5.8 % (by mass)
Porosity	24.7 %
Durability	Can be used externally but consideration should be given to design/detail to minimise exposure to rainwater and rainwater runoff. Some resistance to salt damage
Flexural Strength (3 Point)	8.7 MPa
Flexural Strength (3 Point)	10.6 MPa post 56 cycle freeze thaw
Saturation Co-efficient	0.77
Design Thermal Conductivity	1.7 W (m.k)-1

Email: sales@abcstone.co.uk

Web: www.abcstone.co.uk

Please note that stone is a natural product and all results are indicative and subject to variation.